

View Online at <https://aerobasegroup.com/nsn/8010-01-508-1891>

Application Method:

Brushing as packaged or roller or spraying as is

Quantity Within Each Unit Package:

1.000 gallons

Gloss Designation:

Gloss

Nonvolatile Material Minimum Percentage:

61.0

Basic Formulation Type:

Polyurethane

Rated Drying Time:

30.000 minutes

Color Chip Number:

17925

Volatile Organic Compound In Grams Per Liters:

340.0

Special Features:

Single component; moisture curing; for use as topcoat on metal and concrete surfaces in marine and industrial environments; 30 minute tack free dry time at 75 degrees f; 7 day full cure time

Color:

White

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700