

View Online at <https://aerobasegroup.com/nsn/8010-01-536-2178>

Application Method:

Spraying as is

Quantity Within Each Unit Package:

1.000 gallons

Content Within Each Unit Package:

Consists of 3 parts of component a (epoxy resin in solvents) and 1 part of component b (activator)

Pigment Material Type:

Epoxy resin

Rated Drying Time:

7.000 hours

Special Features:

Application temperature range 68.0 to 95.0 degrees f; humidity type 20.0 to 85.0 percent; pot life 2 hours; dry to fly 72.0 hours at 75.0 degrees f; full cure 7 days at 75.0 degrees f; compatible with all forms of spray equipment; for application on aluminum and composite surfaces prior to top coating

Color:

Yellow, earth

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A09700