

View Online at <https://aerobasegroup.com/nsn/8010-01-536-2178>

**Application Method:**

Spraying as is

**Quantity Within Each Unit Package:**

1.000 gallons

**Content Within Each Unit Package:**

Consists of 3 parts of component a (epoxy resin in solvents) and 1 part of component b (activator)

**Pigment Material Type:**

Epoxy resin

**Rated Drying Time:**

7.000 hours

**Special Features:**

Application temperature range 68.0 to 95.0 degrees f; humidity type 20.0 to 85.0 percent; pot life 2 hours; dry to fly 72.0 hours at 75.0 degrees f; full cure 7 days at 75.0 degrees f; compatible with all forms of spray equipment; for application on aluminum and composite surfaces prior to top coating

**Color:**

Yellow, earth

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A09700