

View Online at <https://aerobasegroup.com/nsn/8010-01-545-9634>

Application Method:

Brushing as packaged or spraying as is

Tempurature Rating:

1200.0 degrees fahrenheit

Features Provided:

Aluminum pigment

Vehicle Material Type:

Silicone or silicone resin

Rated Drying Time:

1.000 hours

Volatile Organic Compound In Grams Per Liter:

500.0

Environmental Attribute Code:

Low volatile organic compound - coatings - marine operations coatings

Special Features:

For use on heated steel surfaces such as superheated steam lines, personnel heaters, rocket launchers, and on other equipment that precludes the use of conventional paint; dual cartridge style container; 750 x 750 milliliter; for use with specialized spray equipment

Color:

Aluminum

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700