## NSN 8010-01-569-6766

Epoxy Embedding Med - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8010-01-569-6766

_		-						
D.	$\mathbf{r}$	М		ct	N	2	m	ο.
	··	u	u	UL	14	а		┖.

Epoxy embedding medium kit

## **Special Features:**

Application: universal embedding medium for semi-and ultrathin sections; polymerization 35, 45, 60 degree celsius for 24 hour each, alternatively 60 degree celsius for 12 hour; include: 45345-epoxy embedding medium 2x250ml, 45347-hardener mna 250ml, 45346-hardener ddsa 250ml, and 45348-accelerator dmp 30 250ml

Shelf L	ife:
---------	------

N/a

**Unit Of Measure:** 

--

Demilitarization:

No