NSN 8010-01-572-6880

Enamel - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8010-01-572-6880

Specific Use:
Ship/boat exterior
Application Method:
Brushing as packaged or roller or spraying as is or spraying after thinning
Quantity Within Each Unit Package:
5.000 gallons
Features Provided:
Low voc
Gloss Designation:
Semigloss
Vehicle Material Type:
Silicone
Rated Drying Time:
30.000 minutes
Color Chip Number:
26008
Volatile Organic Compound In Grams Per Liter:
333.0
Special Features:
Silicone alkyd; high solids; single component; 30 minute dry to touch, 29 hour dry hard time at 77 degrees f; for above water areas
Color:
Gray
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:
A09700