NSN 8010-01-576-2877

Polyurethane Coating - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8010-01-576-2877

| 3.04 |
|--|
| Application Method: |
| Brushing as packaged or spraying as is or spraying after thinning |
| Quantity Within Each Unit Package: |
| 1.000 gallons |
| Features Provided: |
| Lead free and chromate free |
| Gloss Designation: |
| Flat |
| Coloring Method: |
| Pigmented |
| Basic Formulation Type: |
| Polyurethane |
| Rated Drying Time: |
| 30.000 minutes |
| Color Chip Number: |
| 34088 |
| Volatile Organic Compound In Grams Per Liter: |
| 420.0 |
| Environmental Attribute Code: |
| Low volatile organic compound - coatings - metal parts coatings |
| Special Features: |
| Chemical agent resistant coating (carc); single component; polymeric flattening agent; for use as a finish coat on military combat |
| equipment |
| Color: |
| Olive drab |
| Specification Or Standard: |
| 9 type |
| Shelf Life: |
| N/a |
| Unit Of Measure: |
| |
| Demilitarization: |
| Yes - demil/mli |
| Fiig: |

Mil-std (military Standard): Mil-dtl-53039 spec.

A09700