

View Online at <https://aerobasegroup.com/nsn/8010-01-581-6954>

Application Method:

Spraying as is

Gloss Designation:

Semigloss

Basic Formulation Type:

Polyurethane

Rated Drying Time:

4.000 hours

Special Features:

See akzonobel website for curing solutions

Color:

Green, nato infrared

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700