

View Online at <https://aerobasegroup.com/nsn/8010-01-590-4045>

Specific Use:

Aircraft

Application Method:

Spraying after thinning

Gloss Designation:

Gloss

Basic Formulation Type:

Polyurethane

Rated Drying Time:

Between 5.000 hours and 7.000 hours

Color Chip Number:

17875

Volatile Organic Compound In Grams Per Liter:

420.0

Color:

White, insignia

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700

Mil-std (military Standard):

Mil-prf-85285 spec.