

View Online at <https://aerobasegroup.com/nsn/8010-01-599-7689>

End Application:

Apache attack helicopter

Application Method:

Brushing as packaged

Quantity Within Each Unit Package:

30.0 milliliters

Content Within Each Unit Package:

Four 1 ounce bottles with brush cap

Body Strength Designation:

Medium

Basic Formulation Type:

Solvent

Rated Drying Time:

2.0 hours

Product Name:

Protective coating

Special Features:

Film thickness: 0.1-0.25mm per coat; drying time: tack-free in 20 minutes, completely dry in 2 hours, cured in 24 hours (all at room temp); temp operating range: minus 75 to plus 150 degrees c; shelf life: 1 year at plus 24 degrees c.

Color:

Clear

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700