

View Online at <https://aerobasegroup.com/nsn/8010-01-604-5737>

**Specific Use:**

Aircraft surfaces

**Application Method:**

Cold spray

**Rated Drying Time:**

2.0 hours

**Product Name:**

Urethane compatible non-chromated epoxy primer 512x310 / 910x533

**Special Features:**

Application temp: 70-80 degree fahrenheit, application humidity: 20-80 percent r.H., mix rati (by volume): 512x310(base)1 part and 910x533(activator) 1 part; appearance: light gray; shelf life: 12 months from date of manufacture; service temp: negative 65 to 300 degree fahrenheit

**Color:**

Gray, light

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A09700