NSN 8010-01-622-5466

Polyurethane Coating - Page 1 of 1

A09700

Mil-std (military Standard):

Mil-prf-23377 spec.



View Online at https://aerobasegroup.com/nsn/8010-01-622-5466 Specific Use: Aircraft surfaces **Application Method:** Spraying as is **Quantity Within Each Unit Package:** 3.000 gallons **Content Within Each Unit Package:** Consists of component a and component b to equal 2 gallons of topcoat; plus component a and component b to equal 1 gallon of primer **Gloss Designation:** Flat **Rated Drying Time:** 6.000 hours **Color Chip Number:** 36375 **Special Features:** High solids; extended weatherability; topcoat and primer supplied as kit; primer is mil-prf-23377 type 1 (standard pigments), class c2 (strontium chromate based corrosion inhibitors); 340 grams per liter maximum voc for primer, 420 grams per liter maximum voc for topcoat Color: Gray **Specification Or Standard:** 4 type and h class Shelf Life: N/a **Unit Of Measure:** Demilitarization: No Fiig: