

View Online at <https://aerobasegroup.com/nsn/8010-01-641-1902>

Specific Use:

Aircraft surfaces

Application Method:

Spraying as is

Quantity Within Each Unit Package:

1.000 pints

Gloss Designation:

Gloss

Coloring Method:

Pigmented

Rated Drying Time:

Between 5.0 hours and 7.0 days

Product Name:

Polyurethane coating

Volatile Organic Compound In Grams Per Liter:

420.0

Special Features:

Polytetra fluoroethylene filled; abrasion resistant; for use on aircraft control surfases; resistant to hydraulic fluids, aircraft fuel, engine oil, solvents, water and cleaning compounds. Dry time is 5 hrs dry through, 10 hrs dry to fly and 7 days ultimate cure.

Color:

Gray

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700