

View Online at <https://aerobasegroup.com/nsn/8010-01-648-8530>

Specific Use:

Aluminum or corrosion resistive primer on steel

Application Method:

Spraying as is

Quantity Within Each Unit Package:

2.80 pounds

Features Provided:

Flammable

Gloss Designation:

Semigloss

Pigment Material Type:

Epoxy resin and polyamide

Rated Drying Time:

5.0 hours

Product Name:

Epoxy polyamide primer

Special Features:

This product complies with military specification mil-prf-23377g, type-i& ii, class c and n; flash point: 45? F (mixed); mix ratio: 3: 1 by volume; solids by volume: 60% (mixed); theoretical coverage @ 1 mils: approx. 1, 200 sq.Ft/gal; pot life: 4 hours @ 77? F, 50% rh; shelf life: 12 months; temperature: 50 ? F , 100 f (air, surface and material) at least 5 ? Above dew point

Color:

Green, dark or yellow, olive

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A09700

Mil-std (military Standard):

Mil-prf-23377g spec.