

View Online at <https://aerobasegroup.com/nsn/8010-01-648-8530>

**Specific Use:**

Aluminum or corrosion resistive primer on steel

**Application Method:**

Spraying as is

**Quantity Within Each Unit Package:**

2.80 pounds

**Features Provided:**

Flammable

**Gloss Designation:**

Semigloss

**Pigment Material Type:**

Epoxy resin and polyamide

**Rated Drying Time:**

5.0 hours

**Product Name:**

Epoxy polyamide primer

**Special Features:**

This product complies with military specification mil-prf-23377g, type-i& ii, class c and n; flash point: 45? F (mixed); mix ratio: 3: 1 by volume; solids by volume: 60% (mixed); theoretical coverage @ 1 mils: approx. 1, 200 sq.Ft/gal; pot life: 4 hours @ 77? F, 50% rh; shelf life: 12 months; temperature: 50 ? F , 100 f (air, surface and material ) at least 5 ? Above dew point

**Color:**

Green, dark or yellow, olive

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A09700

**Mil-std (military Standard):**

Mil-prf-23377g spec.