

View Online at <https://aerobasegroup.com/nsn/8010-01-650-6559>

**Specific Use:**

Aircraft

**End Application:**

F-22 aircraft

**Application Method:**

Spraying after thinning

**Quantity Within Each Unit Package:**

1.0 quarts

**Gloss Designation:**

Gloss or semigloss

**Nonvolatile Material Minimum Percentage:**

2.0

**Coloring Method:**

Pigmented

**Basic Formulation Type:**

Polyurethane

**Rated Drying Time:**

Between 6.0 hours and 12.0 hours

**Color Chip Number:**

17925

**Volatile Organic Compound In Grams Per Liter:**

24.0

**Volatile Compound Content:**

420.0 grams per liter

**Special Features:**

Storage stability is one year when stored inside between 35-115 degrees f in original, unopened container; full cure time is 14 days; application thickness is 1.7-2.3 mils dry film thickness

**Color:**

White

**Specification Data:**

81349-mil-prf-85285e government specification

**Specification Or Standard:**

H class and qt size and 1 type

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A09700

**Mil-std (military Standard):**

Mil-prf-85285e spec.