NSN 8030-00-165-8577

Resin-acid Metal Pretreatment Coating Compound - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8030-00-165-8577

Quantity Within Each Unit Package:
5.000 gallons
Maximum Effective Time After Mixing:
8.0 hours
Maximum Effective Time After Application:
24.0 hours
Resin Component Ingredients:
Polyvinal-butyral plastic and zinc chromate and magnesium silicate and lamp-black and butyl alcohol and ethyl alcohol
Acid Component Ingredients:
Phosphoric acid and water and ethyl alcohol
Rated Drying Time:
30.000 minutes
Supplementary Features:
5 gallon kit
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
No
Fiig:
A53600
Mil-std (military Standard):
Mil-p-15328 spec.