

View Online at <https://aerobasegroup.com/nsn/8030-00-448-9763>

Physical Form:

Paste

Quantity Within Each Unit Package:

1.000 quarts

Specific Usage Design:

For aircraft firewall applications

Special Features:

Curing time-14 days at room temp, 48 hours at 150 degrees f, 4 hours at 275 degrees f; high temp service

Color:

Green, gray

Material:

Silicone

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0