

View Online at <https://aerobasegroup.com/nsn/8030-00-602-0049>

**Physical Form:**

Paste

**Specific Usage Design:**

For aircraft integral fuel tanks and fuel cell cavities

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

72.000 hours

**Special Features:**

Polysulfide; 2 hour working time

**Color:**

Gray

**Material:**

Rubber synthetic

**Supplementary Features:**

6 ounce base and required amount of curing agent in separate containers

**Specification Or Standard:**

A-2 class

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A536d0