

View Online at <https://aerobasegroup.com/nsn/8030-00-850-0758>

Physical Form:

Paste

Quantity Within Each Unit Package:

3.500 ounces

Specific Usage Design:

For aircraft integral fuel tanks and fuel cell cavities

Features Provided:

Separate catalyst

Rated Drying Time:

48.000 hours

Special Features:

Service temperature range of minus 65 degrees f to plus 250 degrees f; polysulfide; 4 hour working time

Material:

Rubber synthetic

Supplementary Features:

3-1/2 ounce in 6 ounce cartridge

Specification Data:

81343-ams-s-8802 professional/industrial association standard

Specification Or Standard:

2 type and b-4 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0