

View Online at <https://aerobasegroup.com/nsn/8030-01-035-0083>

Physical Form:

Paste

Quantity Within Each Unit Package:

50.000 gallons

Specific Usage Design:

For aircraft integral fuel tanks and fuel cell cavities

Features Provided:

Separate catalyst

Rated Drying Time:

72.000 hours

Special Features:

Service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 360 degrees f; for extrusion gun and spatula application; polysulfide; 2 hour working time

Color:

Gray

Material:

Rubber synthetic

Supplementary Features:

50 gallons base and required amount of curing agent in separate containers

Specification Data:

81343-ams3276 professional/industrial association standard

Specification Or Standard:

B-2 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A536d0