

View Online at <https://aerobasegroup.com/nsn/8030-01-119-7885>

Physical Form:

Paste

Quantity Within Each Unit Package:

1.000 pints

Specific Usage Design:

For aircraft windshields and canopies

Features Provided:

Separate catalyst

Rated Drying Time:

8.000 hours

Special Features:

Service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 275 degrees f; for extrusion gun and spatula application; polysulfide; 2 hour working time

Color:

Black

Material:

Rubber synthetic

Supplementary Features:

12 fluid ounce base and required amount of curing agent in separate containers

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0