

View Online at <https://aerobasegroup.com/nsn/8030-01-195-0655>

**Physical Form:**

Paste

**Quantity Within Each Unit Package:**

1.000 quarts

**Specific Usage Design:**

For aircraft integral fuel tanks and fuel cell cavities

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

90.000 hours

**Special Features:**

Service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 360 degrees f; for extrusion gun and spatula application; polysulfide; 4 hour working time

**Color:**

Gray

**Material:**

Rubber synthetic

**Supplementary Features:**

24 fluid ounce base and required amount of curing agent in separate containers

**Specification Data:**

81343-ams3276 professional/industrial association standard

**Specification Or Standard:**

B-4 class

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A536d0