

View Online at <https://aerobasegroup.com/nsn/8030-01-201-0388>

**General Description:**

Flexible, clear, tough, epoxy film, two part, viscosity at room temp 240 cps, spray, brush or dip application, pot life 6 hrs, shelf life 6 mo at 25 degrees c, hardness shore d 80, cure room temp 48 hrs, 200 degrees f 3 hrs, 250 degrees f 1 hr, color white, for wood, plastic, ceramics, glass, metal, covers 300 sq ft per gal

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No