

View Online at <https://aerobasegroup.com/nsn/8030-01-214-0374>

Physical Form:

Liquid

Specific Usage Design:

For aircraft integral fuel tanks and fuel cell cavities

Rated Drying Time:

4.000 hours

Special Features:

Service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 360 degrees f; polysulfide; 1/4 hour working time

Color:

Gray

Material:

Rubber synthetic

Supplementary Features:

3-1/2 ounce in 6 ounce cartridge

Specification Data:

81343-ams3276 professional/industrial association standard

Specification Or Standard:

B-1/4 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0