

View Online at <https://aerobasegroup.com/nsn/8030-01-238-1913>

Physical Form:

Liquid

Quantity Within Each Unit Package:

5.000 gallons

Specific Usage Design:

Aircraft structural applications

Rated Working Time:

40-60 min w/cg-1303-c hardener and 2-3 hrs w/cg-1303-b hardener

Special Features:

14 hours at 77 degrees f w/cg-1303-c hardener and 4 hours at 77 degrees f plus 1 hour at 200 degrees f plus 1/2 hour at 250 degrees f plus 1/2 hour at 300 degrees f plus 2 hours at 350 degrees f when cg-1303-b hardener is used

Material:

Resin

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0