

View Online at <https://aerobasegroup.com/nsn/8030-01-238-1913>

**Physical Form:**

Liquid

**Quantity Within Each Unit Package:**

5.000 gallons

**Specific Usage Design:**

Aircraft structural applications

**Rated Working Time:**

40-60 min w/cg-1303-c hardener and 2-3 hrs w/cg-1303-b hardener

**Special Features:**

14 hours at 77 degrees f w/cg-1303-c hardener and 4 hours at 77 degrees f plus 1 hour at 200 degrees f plus 1/2 hour at 250 degrees f plus 1/2 hour at 300 degrees f plus 2 hours at 350 degrees f when cg-1303-b hardener is used

**Material:**

Resin

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A536d0