

View Online at <https://aerobasegroup.com/nsn/8030-01-251-7853>

**Physical Form:**

Paste

**Specific Usage Design:**

For aircraft integral fuel tanks and fuel cell cavities

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

24.000 hours

**Special Features:**

Buna-n rubber; 4 hour working time

**Color:**

White

**Material:**

Rubber synthetic

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A536d0