

View Online at <https://aerobasegroup.com/nsn/8030-01-290-5138>

Physical Form:

Paste

Quantity Within Each Unit Package:

2.000 ounces

Specific Usage Design:

For aircraft integral fuel tanks

Rated Drying Time:

8.000 hours

Special Features:

Fast curing; service temperature range of minus 65 degrees f to plus 320 degrees f, intermittent use to 360 degrees f; polythioether; 2 hour working time

Color:

Gray

Material:

Rubber synthetic

Supplementary Features:

2 ounce in 2-1/2 ounce cartridge and required amount of primer in separate container

Specification Data:

81343-ams3277 professional/industrial association standard

Specification Or Standard:

1 type and b-2 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0