

View Online at <https://aerobasegroup.com/nsn/8030-01-322-7275>

Physical Form:

Paste

Quantity Within Each Unit Package:

50.000 gallons

Specific Usage Design:

For aircraft integral fuel tanks and fuel cell cavities

Rated Drying Time:

30.000 hours

Special Features:

Service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 360 degrees f; for extrusion gun and spatula application; polysulfide; 1/2 hour working time

Color:

Gray

Material:

Rubber synthetic

Supplementary Features:

50 gallons base and required amount of curing agent in separate containers

Specification Data:

81343-ams3276 professional/industrial association standard

Specification Or Standard:

B-1/2 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0