

View Online at <https://aerobasegroup.com/nsn/8030-01-325-5588>

**Physical Form:**

Paste

**Specific Usage Design:**

Corrosion protection for aluminum alloys and between dissimilar metals; also for emi/rfi shielding

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

10.000 hours

**Special Features:**

Nickel filled; electrically conductive; service temperature range of minus 67 degrees f to plus 250 degrees f, intermittent use to 360 degrees f; polythioether; 2 hour working time

**Color:**

Black

**Material:**

Rubber synthetic

**Supplementary Features:**

6 ounce cartridge

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A536d0