

View Online at <https://aerobasegroup.com/nsn/8030-01-363-9358>

Physical Form:

Paste

Specific Usage Design:

For aircraft integral fuel tanks and fuel cell cavities

Features Provided:

Separate catalyst

Rated Drying Time:

40.000 hours

Special Features:

Premixed and frozen; must be shipped and stored at minus 40 degrees f; polysulfide; 2 hour working time

Material:

Rubber synthetic

Supplementary Features:

4-1/2 ounce in 6 ounce cartridge

Specification Data:

81343-ams-s-8802 manufacturers specification

Specification Or Standard:

2 type and b-2 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0