

View Online at <https://aerobasegroup.com/nsn/8030-01-364-0255>

Physical Form:

Paste

Specific Usage Design:

For aircraft integral fuel tanks and fuselage sealing applications

Features Provided:

Separate catalyst

Rated Drying Time:

12.000 hours

Special Features:

Service temperature range of minus 80 degrees f to plus 320 degrees f, intermittent use to 420 degrees f; for extrusion gun and spatula application; polythioether; 2 hour working time

Color:

White

Material:

Rubber synthetic

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0