

View Online at <https://aerobasegroup.com/nsn/8030-01-364-0256>

**Physical Form:**

Paste

**Specific Usage Design:**

For aircraft windshields and canopies

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

3.000 hours

**Special Features:**

Service temperature range of minus 80 degrees f to plus 320 degrees f, intermittent use to 420 degrees f; for extrusion gun and spatula application; polythioether; 1/2 hour working time

**Color:**

Gray

**Material:**

Rubber synthetic

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A536d0