

View Online at <https://aerobasegroup.com/nsn/8030-01-364-3885>

Physical Form:

Paste

Quantity Within Each Unit Package:

3.500 ounces

Specific Usage Design:

For aircraft integral fuel tanks

Features Provided:

Separate catalyst

Rated Drying Time:

4.000 hours

Special Features:

Fast curing; service temperature range of minus 65 degrees f to plus 320 degrees f, intermittent use to 360 degrees f; primer not required; polythioether; 1/2 hour working time

Color:

White

Material:

Rubber synthetic

Supplementary Features:

3-1/2 ounce in 6 ounce cartridge

Specification Data:

81343-ams3277 professional/industrial association standard

Specification Or Standard:

2 type and b-1/2 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A536d0