

View Online at <https://aerobasegroup.com/nsn/8030-01-364-7359>

Physical Form:

Paste

Quantity Within Each Unit Package:

2.250 ounces

Specific Usage Design:

For aircraft firewall applications

Rated Drying Time:

4.000 hours

Volatile Organic Compound In Grams Per Liter:

360.0

Special Features:

Primerless; service temperature range of minus 65 degrees f to plus 400 degrees f, and flash temperatures up to 2000 degrees f; 2 hour working time

Color:

Black

Material:

Rubber synthetic

Supplementary Features:

2-1/4 ounce in 2-1/2 ounce cartridge

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0