

View Online at <https://aerobasegroup.com/nsn/8030-01-374-9056>

**Basic Ingredient:**

Molybdenum disulfide

**Quantity Within Each Unit Package:**

1.000 pints

**Usage Design:**

Solid film lubricant for high temperature and high pressure applications

**Special Features:**

Water based; gray; liquid; silicate binder; thermally cured; cure time is 2 hours at 175 degrees f, then 2 hours at 400 degrees f

**Supplementary Features:**

1 pint can

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A535n0