

View Online at <https://aerobasegroup.com/nsn/8030-01-374-9056>

Basic Ingredient:

Molybdenum disulfide

Quantity Within Each Unit Package:

1.000 pints

Usage Design:

Solid film lubricant for high temperature and high pressure applications

Special Features:

Water based; gray; liquid; silicate binder; thermally cured; cure time is 2 hours at 175 degrees f, then 2 hours at 400 degrees f

Supplementary Features:

1 pint can

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A535n0