

View Online at <https://aerobasegroup.com/nsn/8030-01-378-4546>

**Physical Form:**

Paste

**Specific Usage Design:**

For aircraft integral fuel tanks and fuselage sealing applications

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

30.000 hours

**Special Features:**

Service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 275 degrees f; polysulfide; 1 hour working time

**Color:**

Brown

**Material:**

Rubber synthetic

**Supplementary Features:**

50 gallons base and required amount of curing agent in separate containers

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A536d0