

View Online at <https://aerobasegroup.com/nsn/8030-01-380-9542>

Physical Form:

Paste

Quantity Within Each Unit Package:

1.500 ounces

Specific Usage Design:

For aircraft integral fuel tanks and fuel cell cavities

Rated Drying Time:

72.000 hours

Special Features:

Premixed and frozen; must be shipped and stored at minus 40 degrees f; service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 360 degrees f; polysulfide; 2 hour working time

Color:

Gray

Material:

Rubber synthetic

Supplementary Features:

1-1/2 ounce in 2 ounce cup

Specification Data:

81343-ams3276 professional/industrial association standard

Specification Or Standard:

B-2 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536d0