

View Online at <https://aerobasegroup.com/nsn/8030-01-386-3889>

Physical Form:

Paste

Specific Usage Design:

For aircraft integral fuel tanks and fuel cell cavities

Features Provided:

Separate catalyst

Rated Drying Time:

40.000 hours

Special Features:

Premixed and frozen; must be shipped and stored at minus 40 degrees f; service temperature range of minus 65 degrees f to plus 250 degrees f; polysulfide; 2 hour working time

Material:

Rubber synthetic

Supplementary Features:

1 ounce in 2-1/2 ounce cartridge

Specification Data:

81343-ams-s-8802 manufacturers specification

Specification Or Standard:

2 type and a-2 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A536d0