

View Online at <https://aerobasegroup.com/nsn/8030-01-386-3889>

**Physical Form:**

Paste

**Specific Usage Design:**

For aircraft integral fuel tanks and fuel cell cavities

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

40.000 hours

**Special Features:**

Premixed and frozen; must be shipped and stored at minus 40 degrees f; service temperature range of minus 65 degrees f to plus 250 degrees f; polysulfide; 2 hour working time

**Material:**

Rubber synthetic

**Supplementary Features:**

1 ounce in 2-1/2 ounce cartridge

**Specification Data:**

81343-ams-s-8802 manufacturers specification

**Specification Or Standard:**

2 type and a-2 class

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A536d0