

View Online at <https://aerobasegroup.com/nsn/8030-01-461-2621>

**Physical Form:**

Liquid

**Specific Usage Design:**

Sealing fuel tanks and pressurized cabins

**Curing Method:**

Air dried or heat

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

30.000 hours

**Special Features:**

10/1 base/accelerator mixing ratio; 90 pct nonvolatile content; polysulfide liquid polymer compound; 20 pa, s brookfield viscosity no. 4 at 10 rpm; 45 degrees shore a hardness; -75 to 105 degrees c; can apply heat up to 50 degrees c for faster curing

**Color:**

Brown, red

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A536d0