

View Online at <https://aerobasegroup.com/nsn/8030-01-464-3560>

Physical Form:

Paste

Specific Usage Design:

For aircraft integral fuel tanks and fuselage sealing applications

Features Provided:

Separate catalyst

Rated Drying Time:

24.000 hours

Special Features:

Service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 360 degrees f; polysulfide; 2 hour working time

Color:

Gray

Material:

Rubber synthetic

Supplementary Features:

100 cc cartridge

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A536d0