

View Online at <https://aerobasegroup.com/nsn/8030-01-464-3562>

**Physical Form:**

Paste

**Specific Usage Design:**

For aircraft integral fuel tanks

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

24.000 hours

**Special Features:**

Service temperature range of minus 65 degrees f to plus 250 degrees f, intermittent use to 360 degrees f; polysulfide; 2 hour working time

**Color:**

Gray

**Material:**

Rubber synthetic

**Supplementary Features:**

500 cc cartridge

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A536d0