

View Online at <https://aerobasegroup.com/nsn/8030-01-485-5137>

**Tempurature Rating:**

250.0 degrees fahrenheit

**End Application:**

F-22 acft

**Physical Form:**

Paste

**Quantity Within Each Unit Package:**

2.500 ounces

**Specific Usage Design:**

Integral fuel tank sealing

**Curing Method:**

Air dried

**Rated Working Time:**

2 hours

**Features Provided:**

Separate catalyst

**Rated Drying Time:**

24.000 hours

**Special Features:**

Material is manganese dioxide cured permapol p-5 modified polysulfide; extrusion gun or spatula application; service temperature range -65 degrees f to 250 degrees f w/intermittent excursions to 360 degrees f; resistant to salt water, hydrocarbons, fungus, water, alcohols, petroleum-base and synthetic lubricating oils, and petroleum-base hydraulic fluids

**Color:**

Gray

**Material:**

Plastic

**Supplementary Features:**

Full cure 14 days at 77 degrees f w/50 pct relative humidity

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A536d0