

View Online at <https://aerobasegroup.com/nsn/8030-01-485-5137>

Tempurature Rating:

250.0 degrees fahrenheit

End Application:

F-22 acft

Physical Form:

Paste

Quantity Within Each Unit Package:

2.500 ounces

Specific Usage Design:

Integral fuel tank sealing

Curing Method:

Air dried

Rated Working Time:

2 hours

Features Provided:

Separate catalyst

Rated Drying Time:

24.000 hours

Special Features:

Material is manganese dioxide cured permapol p-5 modified polysulfide; extrusion gun or spatula application; service temperature range -65 degrees f to 250 degrees f w/intermittent excursions to 360 degrees f; resistant to salt water, hydrocarbons, fungus, water, alcohols, petroleum-base and synthetic lubricating oils, and petroleum-base hydraulic fluids

Color:

Gray

Material:

Plastic

Supplementary Features:

Full cure 14 days at 77 degrees f w/50 pct relative humidity

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A536d0