

View Online at <https://aerobasegroup.com/nsn/8030-01-507-0260>

**End Application:**

Used on t-6a training aircraft

**Features Provided:**

Separate accelerator

**Rated Drying Time:**

24.000 hours

**Special Features:**

Low density fiberglass reinforced syntactic foam insulates, provides structure and fire resistance; 3 part component system: part a, pale blue phenolic, 100 parts by wt; part b red liquid catalyst, 6 parts by wt; part c white granular accelerator, 20 parts by wt; designed for trowel application

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A536f0