

View Online at <https://aerobasegroup.com/nsn/8030-01-507-0260>

End Application:

Used on t-6a training aircraft

Features Provided:

Separate accelerator

Rated Drying Time:

24.000 hours

Special Features:

Low density fiberglass reinforced syntactic foam insulates, provides structure and fire resistance; 3 part component system: part a, pale blue phenolic, 100 parts by wt; part b red liquid catalyst, 6 parts by wt; part c white granular accelerator, 20 parts by wt; designed for trowel application

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536f0