

View Online at <https://aerobasegroup.com/nsn/8030-01-536-6303>

Quantity Within Each Unit Package:

1.000 quarts

Special Features:

Curing agent for various epoxy resins; used with rf-4010 and rf-5407; 20 minute pot life; cure room temperature or 3 hours at 150 degrees fahrenheit; faint yellow liquid; mild ammonioal odor; 840 degrees fahrenheit auto ignition temperature; stable

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A536p0